

EU-041**201706112****06.11.2017****Overall Rating / Test Sonucu :** **SUCCESS / GEÇER**

Report No/ Rapor No : 201706112 - 1
Applicant/Deney Sahibi : **RAMADA ULUSLARARASI TİCARET A.Ş.**
Applicant Address / Adres : Adalet Mah. Anadolu Cad. No:41 / 1 Kat:10 Megapol Tower 35530 Bayraklı / İzmir / Türkiye
Contact Person / Yetkili : Not specified
Contact Telephone / Telefon: +90 232 999 49 39
Contact e-mail / E-Posta: info@ramadashade.com
Sample Accepted on / Numune Tarihi : 25.10.2017 : 11:40
Report Date / Rapor Tarihi : 06.11.2017
Total number of pages / Rapor Sayfa : 3 (Pg/Syf)

Sample ID : BEJ GÖLGELİK 1**Rates / Açıklamalar:** **PE ORGANIC SHADE FABRIC / PE ÖRGÜLÜ GÖLGELİK KUMAŞ**

	TEST	METHOD	Permeability / Geçirgenlik	UV protective / UV Koruma
*	Textiles. Solar UV protective properties. Method of test for apparel fabrics. Tekstil. Güneş UV koruyucu özellikleri. Tekstil kumaşları için test metodu	EN 13758-1:2002	%5.38	> 95




Test results, methods and other information about the sample shown in the relevant pages of this Report are based on the information specified in accordance with "Test Request Form (PR03-F01)" conveyed to us from the Applicant. Test results are valid for the sample as identified above. Sample may not represent the lot which it belongs. This Report does not replace a Product Certificate. Full report or any part of it may not be reproduced or used for any other purpose without the written permission of Azolab Laboratory. Sampling has not been done by us. Unsigned and unsealed Reports are invalid. Analysis as indicated with "*" are in the scope of our Accreditation Certificate issued from TURKAK according to TS EN ISO/IEC 17025. Analysis as indicated with "****" are performed at the external laboratories using accredited test methods according to TS EN ISO/IEC 17025 from TURKAK. Possible extra notes may add with starting "N" to related pages. Tested and remaining samples will be kept in specified terms & conditions at test request and/or proposal form. Physically, chemically and microbiologically decomposed samples are discarded regardless of the storage period. Applicant can not claim any right in this regard. Results are shown in this Report do not include Measurement Uncertainty values. Measurement Uncertainty values are not taken in consideration during Pass/Fail assessment of test results shown in this Report. Evaluation of the test results using Measurement Uncertainty values is the responsibility of the Applicant.

RESULT / SONUÇ

Number of Specimens Analysed / Analiz Edilen Numunelerin Sayısı : 4
Mean UVA Transmission / Ortalama UVA İletimi : 5.38%
Mean UVB Transmission / Ortalama UVB İletimi : 0.03%
Ultraviolet Radiation Blocked / Ultraviyole Radyasyon Engelleme : 99%

Protection Factor Results / Koruma Faktörü Sonuçları

Mean of all Measurements: 356
Standard Deviation : 27
Protection Factor : 329



Test equipment / Test Ekipmanı

EUROLAB EL / UV IR VL (Calibration was made on 23.08.2017) /

Mean UVB Transmission: The average UVB radiation (290 to 315 nm) passing through the test specimens.

EUROLAB EL UV IR VL Test Makinası (Kalibrasyon 23.08.2017 tarihinde yapılmıştır)



SAMPLE PICTURE UNDER TEST / Test Edilen Ürün Resmi

